



1. Gloss measurement of lacquered aluminum plates

The gloss factor of lacquered aluminum plates should be measured. For this purpose, a gloss sensor type **GLOSS-15-60°** is used. At this, the distance from the gloss sensor to the object is approximately 15mm and the spot size at this distance is around 20mm x 10mm (elliptical in shape). The gloss factor can be properly measured, as shown in the screen shots.

